

EP04/51252



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

REC'D 14 OCT 2004

WIPO POT

Bescheinigung

Certificate

Attestation

Die angehefteten Unterla-
gen stimmen mit der
ursprünglich eingereichten
Fassung der auf dem näch-
sten Blatt bezeichneten
europäischen Patentanmel-
dung überein.

The attached documents
are exact copies of the
European patent application
described on the following
page, as originally filed.

Les documents fixés à
cette attestation sont
conformes à la version
initialement déposée de
la demande de brevet
européen spécifiée à la
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

03102245.2

**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

EPO - DG 1
30. 09. 2004
(76)

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk

BEST AVAILABLE COPY



Europäisches
Patentamt

European
Patent Office

PCT/EP200 4 / 0 5 1 2 5 2

Office européen
des brevets

30.09.04

Anmeldung Nr:
Application no.: 03102245.2
Demande no:

Anmeldetag:
Date of filing: 22.07.03
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

N.V. BEKAERT S.A.
Bekaertstraat 2
8550 Zwevegem
BELGIQUE

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se referer à la description.)

Hybrid high-elongation cord

In Anspruch genommene Priorität(en) / Priority(ies) claimed /Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

D07B1/00

Am Anmeldetag benannte Vertragsstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LU MC NL
PT RO SE SI SK TR LI

Field of the invention.

The present invention relates to an elongation steel cord adapted for the reinforcement of elastomer structures, more particularly adapted for the reinforcement of the outermost plies of rubber tires.

5

Background of the invention.

Elongation cords, such as high-elongation cords, are used to reinforce the belt of a radial tire. This can be the radially outermost ply, also called a protection ply, or an intermediate layer. The protection ply is the ply which lies closest to the tread and thus to the surface. As a direct result of its position in a tire and as its name says, a protection ply fulfills a front line function in the protection of a tire: Every unevenness and every roughness on the roads are first felt and taken up by the protection ply.

10
15
20
The elongation cord can also be used in other parts of the belt as strips or covering the whole width of the belt. Very often the elongation cords are used under a nearly 0° angle with respect to the equatorial plane of the tire, so in a circumferential direction. In this way the elongation cord can stabilize the belt edges and also control the belt deformation e.g. in case of a wide belt (low aspect ratio tire). A typical example for that is the so-called super single drive axle tire, this is one single wide tire replacing the normal 2 tires on every side that transmit the motor power of a truck to the road.

25
Consequently, severe requirements are put on cords reinforcing these protection plies.

First of all, the elongation cords must have a high corrosion resistance, since moisture that is able to penetrate via cracks in the tread is most likely to arrive first at the protection ply. Full rubber penetration is a way to slow down the corrosion attack on steel cords. The elongation cords must have – as their name expresses it – a high elongation before they break.

30
35
Thirdly, the elongation cords must allow an easy manufacture of the tires when they are used under a nearly 0° angle with respect to the equatorial plane. For that reason a high elongation at low loads is required in order to follow the tire expansion when the green tire is lifted in the tire mould for vulcanization. If this low load elongation is

no present, the elongation cords risk to get into contact with steel cord of other plies.

Finally, the elongation cords must be cheap in manufacture.

5 An example of a high-elongation cord is the well-known 3x7x0.22 SS high-elongation (HE) steel cord with an elongation at fracture of about 7.5%.

Such a cord, however, is expensive to manufacture, due to its multi-strand construction and due to their small twisting steps, which are
10 required to make the steel cord construction springy and obtain the final elongation.

The prior art has already provided alternative cords which provide the required elongation at fracture and which are less costly from a
15 manufacturing point of view. However, while providing a cheaper alternative, prior art cords do not provide a good rubber penetration.

Summary of the invention.

20 It is an object of the present invention to avoid the drawbacks of the prior art.

It is another object of the present invention to provide an alternative for a high-elongation cord.

It is yet another object of the present invention to provide a cord with
25 a full rubber penetration.

It is a further object of the present invention to provide an elongation cord, which allows for an easy manufacture of the tire.

According to the invention there is provided an elongation cord
30 adapted for the reinforcement of elastomer structures. The steel cord comprises a core and three to nine strands twisted around the core with a cord-twisting step in a cord twisting direction. The core is a polymer core in order to provide the required elongation at fracture.
At least one of the strands - and preferably more than one strand,
35 and most preferably all of the strands - comprises a first group of

5 filaments and a second group of filaments. These filaments are preferably steel filaments. The first group of filaments is twisted with a first twisting step in a first twisting direction. The second group of filaments is twisted with a second twisting step in a second twisting direction. The first group of filaments is different from the second group of filaments in that either the first twisting step is different from the second twisting step, or the first twisting direction is different from the second twisting direction, or both.

10 The first twisting direction is equal to the cord twisting direction and the first twisting step is equal to the cord twisting step.

The first group of filaments may comprise between two and five filaments. The second group of filaments may comprise between one and five filaments.

15 Following combinations are possible:

	2+1	3+1	4+1	5+1
	2+2	3+2	4+2	5+2
	2+3	3+3	4+3	5+3
	2+4	3+4	4+4	5+4
20	2+5	3+5	4+5	5+5

It is hereby understood that the first number is the number of filaments of the first group and the second number is the number of filaments of the second group.

25 The polymer for the core may be selected amongst:

- A thermoplastic polyester based on polybutylenterephthalat or on polyetheleneterephthalat;
- A copolyester;
- A thermoplastic polyurethane; and
- 30 - A polyamide.

The polymer is preferably a polyester or a polyamide.

35 The invention cord has a structural elongation (blank, i.e. not embedded in rubber) of at least 1.20%, e.g. at least 1.30. Such a relatively high level of structural elongation – at low or even no-

existing loads - facilitates the manufacturing of the tire since it prevents the elongation cords in the outermost protection layer from contacting the steel cords in the rubber plies immediately under the protection layer.

5

The invention cord has an elongation at break (blank, i.e. not embedded in rubber) of at least 5%.

An example of a cord according to the invention is:

10

0.45 polyamide + 4 x (3x0.23 + 2x0.23)

0.45 mm is the initial diameter of the polyamide core
the pitch of the second group of two filaments in the
final cord is 4.6 mm;

15

the pitch of the first group of three filaments in the
final cord and of the final cord is 6.0 mm.

Preferably the polymer core has a thickness, which is at least equal to or greater than the smallest diameter of the filaments in the first group or in the second group.

20

Most preferably, the polymer core has a thickness, which is at least equal to or greater than two times the smallest diameter of the filaments in the first group or in the second group.

The thicker the polymer core, the higher the structural elongation and the higher the elongation at break.

25

Brief description of the drawings.

The invention will now be described into more detail with reference to the accompanying drawings wherein

30

- FIGURE 1 is a schematic drawing of a cross-section of an elongation cord according to the invention;
- FIGURE 2 is a cross-section of an effectively made elongation cord according to the invention;
- FIGURE 3 shows a typical stress-elongation curve of an invention cord.

35

Description of the preferred embodiments of the invention.

5 FIGURE 1 shows a schematic drawing of a hybrid elongation cord 10 according to the invention. The elongation cord 10 has a polyester core 12. Four strands 14 have been twisted around core 12. Each strand 14 has two groups of steel filaments: A first group 16 with steel filaments 17 and 18 and a second group 20 with steel filaments 21 and 22. The twisting pitch of the filaments 17 and 18 in the first group 16 is equal to the twisting pitch of the strands 14 around the polyester core 12. The twisting direction of the filaments 17 and 18 in the first group 16 is equal to the twisting direction of the strands 14 around the polyester core 12.

15 A hybrid elongation cord 10 can be manufactured as follows. First of all, the stranding takes place: All the strands 14 are manufactured individually and in advance. The way of manufacturing the strands 14 has been disclosed in US-A-4,408,444. The result is a strand with two groups of steel filaments:

- 20 - A first group of steel filaments 17, 18 which are untwisted or nearly untwisted, i.e. with a twisting step of more than 200 mm;
- A second group of steel filaments 21, 22 that are twisted around each other filaments with a same twisting step and in a same twisting direction as they are twisted around the first group of steel filaments.
- 25

 In a second step, the strands 14 are twisted around the polymer core 12 by means of a double-twisting device (often called buncher). Since the steel filaments 17, 18 out of the first group 16 have a twisting step between 200 mm and an infinite value; this first group takes about the same twisting step and twisting direction as the twisting step and the twisting direction of the final cord 10.

30

 FIGURE 2 shows a more realistic picture of a cross-section of an effectively made elongation cord according to the invention. The steel cord 10 has a polyester core 12, which is no longer exact

35

5 circular. The individual strands 14 around the polymer core 12 are not so easy to distinguish from one another and the filaments inside each strand of the first group and of the second group are no longer to be distinguished from each other, at least not from one single cross-section. The filaments show a more elliptic cross-section as they are twisted around the polymer core 12. Rubber 26 is able to penetrate everywhere between the individual filaments.

Comparison tests.

10 Following cord has been used as reference cord:

REF 4 x (3x0.22 + 2x0.22) 4.5 / 6.0 SS without polymer core

4.5 mm is the strand twisting step in the final cord of the filaments of the second group

15 6.0 mm is the strand-twisting step in the final cord of the filaments of the first group and is also the final cord twisting step.

This reference cord is compared with following invention cords:

INV1 PET core 0.22 mm + 4 x (3x0.22 + 2x0.22) 4.5/6.0 SS

INV2 PET core 0.28 mm + 4 x (3x0.22 + 2x0.22) 4.5/6.0 SS

20 INV3 Polyamide core 0.45 mm + 4 x (3x0.22 + 2x0.22) 4.5/6.0 SS

	REF	INV1	INV2	INV3
Optical diameter (mm)	1.379	1.401	1.413	1.497
Tensile test blank				
Breaking load Fm (Newton)	1644	1693	1694	1658
Tensile strength Rm (MPa)	2010	2006	2000	1887
Total elongation at fracture Ats (%)	4.83	5.55	5.62	6.48
Structural elongation Ax (%)	1.14	1.31	1.41	1.78
E-modulus (MPa)	90043	81071	82232	62981

Tensile test embedded				
Breaking load Fm (Newton)	1642	1769	1695	1711
Tensile strength Rm (MPa)	2008	2096	2001	1948
Total elongation at fracture A_{ts} (%)	2.28	3.08	3.03	3.55
Structural elongation A_x (%)	0.24	0.46	0.56	0.72
E-modulus (MPa)	114312	102469	93268	84589

With increasing thickness of the polymer core, the E-modulus decreases while both the total elongation at fracture or break and the structural elongation increase.

5

INV3 has been experienced as the better invention cord.

FIGURE 3 shows a tensile stress – elongation curve 30 of this invention cord INV3. This curve 30 can be divided in three main parts. A first part is a non-linear part and has high elongations at low tensile stresses; this is the part of structural elongation. A second part is the middle part and is linear. This part occurs in the elastic field and follows the law of Hooke. The corresponding elongation is the elastic elongation. The third part is non-linear and is the plastic part. The third part is characterized by a saturation phenomenon. The E-modulus is the slope of the line 32, which coincides with the linear part. The structural elongation A_x is the value on the abscissa value where the line 32 intersects with the abscissa axis.

20

In a broader perspective, the steel filaments of a hybrid elongation cord according to the invention usually have a diameter ranging from 0.03 mm to 0.80 mm, and preferably from 0.05 mm to 0.45 mm. The steel filaments have a composition which is along the following lines: a carbon content ranging from 0.60 to 1.15 %, a manganese

5 content ranging from 0.10 to 1.10 %, a silicon content ranging from 0.10 to 0.90 %, sulfur and phosphorous contents being limited to 0.15 %, preferably to 0.010 %; additional elements such as chromium (up to 0.20 -0.40 %), copper (up to 0.20 %), nickel (up to 0.30 %), cobalt (up to 0.20 %) and vanadium (up to 0.30 %) may be added.

10 The final tensile strength Rm of the filaments depends upon its diameter: for example, a 0.2 mm normal tensile filament has a Rm of above about 2800 Mega Pascal (MPa), a 0.2 mm high tensile filament has a Rm of above about 3400 MPa, a 0.2 mm super high tensile filament has a Rm of above about 3600 MPa and a 0.2 mm ultra high tensile filament has a Rm of above about 4000 MPa.

15 For the highest tensile strengths, the following steel composition is suitable: a carbon content ranging from 0.90 % to 1.10 %, a silicon content below 0.40 %, a manganese content below 0.50 % and a chromium content ranging from 0.10 % to 0.30 %.

20 The steel filaments are coated with a layer that promotes the adhesion to the rubber: copper alloy coatings such as brass (either low - 63.5 % Cu - and high copper - 67.5 % Cu) or a complex brass coating (Ni + brass, brass + Co ...). Zinc coatings treated with silanes for rubber adhesion are also possible.

25

CLAIMS

1. An elongation cord adapted for the reinforcement of elastomer structures,
5 said steel cord comprising
 a core and
 three to nine strands twisted around said core with a cord
twisting step in a cord twisting direction,
said core being a polymer core,
10 **characterized in that**
 at least one of said strands comprises a first group of filaments
and a second group of filaments,
said first group of filaments being twisted with a first twisting step
in a first twisting direction,
15 said second group of filaments being twisted with a second
twisting step in a second twisting direction,
said first twisting step being different from said second twisting
step or said first twisting direction being different from said
second twisting direction, or both,
20 said first twisting direction being equal to said cord twisting
direction, and said first twisting step being equal to said cord
twisting step.
- 25 2. A cord according to claim 1 wherein said first group of filaments
comprises between two and five filaments.
- 30 3. A cord according to any one of the preceding claims wherein said
second group of filaments comprises between one and five
filaments.
- 35 4. A cord according to any one of the preceding claims wherein said
polymer is polyester or polyamide.
5. A cord according to any one of the preceding claims wherein all of
said strands comprise such a first group of filaments and such a

second group of filaments.

5

6. A cord according to any one of the preceding claims wherein said cord has a structural elongation of at least 1.20%.

7. A cord according to any one of the preceding claims wherein said cord has an elongation at break of at least 5%.

10

8. A cord according to any one of the preceding claims wherein said polymer core has a thickness which is equal or greater to the smallest diameter of the filaments in said first group or in said second group.

15

9. A cord according to claim 8 wherein said polymer core has a thickness which is equal or greater to two times the smallest diameter of the filaments in said first group or in said second group.

20

ABSTRACT:

5 An elongation cord (10) adapted for the reinforcement of elastomer
structures has a polymer core (12) and three to nine strands (14)
twisted around the core with a cord twisting step in a cord twisting
direction. At least one of the strands (14) has a first group (16) of
filaments (17, 18) and a second group (20) of filaments (21, 22).
10 The first group (16) of filaments (17, 18) is twisted with a first
twisting step in a first twisting direction and the second group (20) of
filaments (21, 22) is twisted with a second twisting step in a second
twisting direction. The first twisting step is different from the second
twisting step or the first twisting direction is different from the second
twisting direction, or both. The first twisting direction is equal to the
cord twisting direction and the first twisting step is equal to the cord
15 twisting step.




Fig. 1




Fig. 2




Fig. 3

PCT/EP2004/051252



**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☐ **BLACK BORDERS**

☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**

☐ **FADED TEXT OR DRAWING**

☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**

☒ **SKEWED/SLANTED IMAGES**

☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**

☐ **GRAY SCALE DOCUMENTS**

☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**

☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**

☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.